



Arden Moly 2 Grease

Non-Soap Grease with Solid Lubricants
Previous Name: Armol 2

Product Description:

Veedol Arden Moly 2 is a premium quality non-melting inorganic clay-based grease containing high viscosity base oil, performance additives and solid lubricant.

The inorganic thickener makes this grease suitable for applications at extremely high temperatures. It has very good oxidation stability and good adhesive properties. Fortified with special additives Veedol Armol ensures protection against rust, corrosion, and wear. Also, the solid lubricant molybdenum disulfide (MoS₂) helps to withstand heavy and shock loads by providing continuous lubricating film.

Features/Benefits:

- **Super fine solid lubricant MoS₂** provides excellent protection against wear in case of accidental grease loss or overheating.
- **Excellent high temperature resistance** makes this grease suitable for high temperature applications.
- **High load carrying capacity** enables to withstand heavy and shock loads.
- **Excellent oxidation resistance** at high temperature helps reducing formation of harmful deposits.

Application:

- Heavy duty, high temperature, slow moving industrial applications.
- Ideal for use in metal working autoclaves, kiln. Also suitable for underground mining equipment.
- Drying oven, conveyor bearings, hot-mix plant bearing lubrication.
- Hinges, chains, and pins operating under high temperature.
- Operating temperature range -10°C to +200°C.
- Can be used above 200°C with increased re-greasing interval. Re-greasing interval to be determined by the user.



Arden Moly 2 Grease
Non-Soap Grease with Solid Lubricants
Previous Name: Armol 2

Typical Properties:

Properties	Test method	Arden Moly 2 Grease
NLGI Grade		2
Soap / Thickener type		Non-Soap, Clay
Appearance	Visual	Smooth, buttery
Color	Visual	Dark Grey
Worked penetration 60 double strokes @25°C	ASTM D217	283
Penetration 10,000 double strokes	ASTM D217	308
Dropping point, °C	ASTM D2265	>300
Base oil properties-		
a. Kinematic Viscosity @ 40°C, cSt	ASTM D445	460
b. Kinematic Viscosity @ 100°C, cSt		30
Copper strip corrosion at 100°C for 24 hrs.	ASTM D4048	Negative
Water washout @80°C, %	ASTM D1264	4.4
Leakage tendency, by mass, g	ASTM D1263	5.0
Solid lubricant		MoS ₂

The above typical properties are those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice.

STORAGE:

All packages should be stored under cover. It should not be exposed to direct sunlight, intense cold and extreme temperature fluctuations. Where outside storage is unavoidable, drums should be laid horizontally or properly covered to avoid the possible ingress of water and damage to drum markings.

HEALTH AND SAFETY:

The information on this product is available in the Material Safety Data Sheet (MSDS) as a guide to the precautions and safe handling of this product and its disposal. For further information, we recommend you review the MSDS. If handled correctly, there are no special precautions suggested.