



VEEDOL SOLUCUT

WATER MISCIBLE METAL WORKING FLUID BORON FREE

BUILT IN LUBRICITY ENHANCER

Performance Features & Benefits



Nitrite, Boron & Triazine Biocide free
Free from hazardous chemical, reduced risk of operators health & safety.



Chlorine, Sulphur and phosphorous-free
Make it environmentally friendly, low disposal cost.



Excellent Emulsion Stability
Tolerant to difficult diluent water with hardness upto 500 ppm.



Excellent Metal Passivation
It provide good corrosion protection for Aluminium and non-ferrous metals.



Excellent Field Performance
Soft foaming in salt water.



Corrosion Inhibition
Corrosion protection for ferrous provide excellent tool life and surface finish.

Materials

- » Ferrous alloys
- » Aluminium alloys
- » Copper and yellow metal alloys
- » Oil-resistant plastics & non-ferrous materials

Please follow equipment manufacturer's recommendations for performance level and viscosity grade.

Typical Recommended Concentrations

| | |
|-------------------------------|---------|
| General machining | 5 - 7% |
| Thread cutting and forming | 6 - 8% |
| Deep hole drilling and boring | 8 - 10% |
| Reaming | 8 - 12% |
| Grinding | 3 - 5% |

The concentrations vary depending on the type of machining operations.

Product Mixing

TWOCIL advises the use of automated mixing systems. If mixing manually, always add the concentrate to the water with maximum agitation. If water is added to the concentrate, the emulsions may prove unstable. Avoid mixing with very cold concentrate or water.

Product Management

The working concentrations should be carefully controlled and monitored daily as higher & lower working concentrations will have performance, health and safety implications.



Typical Properties

| | |
|--|-------------------|
| Appearance | Amber Liquid |
| Stability (0°C/Ambient/50°C) | Passes |
| Emulsion Type @ 5% in tap water | Milky |
| Cast Iron Corrosion IP 287, 5.0 % in 200 ppm | Passes |
| pH @ 5% in deionized water | 9.5 |
| Defoam in 50 ppm water | Nil in 60 seconds |
| Refractometer Factor | 1.0 |

The above typical properties are those obtained with normal production tolerance and do not constitute as specification. Variations that do not affect product performance are to be expected during normal manufacturing processes and at different blending locations. The information contained herein is subject to change without notice.



VEEDOL SOLUCUT

WATER MISCIBLE METAL WORKING FLUID BORON FREE

BUILT IN LUBRICITY ENHANCER

Fluid Maintenance



Poor or incorrect emulsion preparation may lead to instability and could considerably shorten the life of the emulsion. Prior to making any fresh emulsion, it is highly recommended to use compatible system cleaner for purging the machine tool coolant system.

Storage



Store inside the warehouse, ideally between 10°C and 35°C. Shelf life is 12 months from date of manufacture. All packages should be stored under cover. It should not be exposed to direct sunlight, intense cold and extreme temperature fluctuations. Where outside storage is unavoidable, drums should be laid horizontally or properly covered to avoid the possible ingress of water and damage to drum markings.

Health, Safety and Environment



The information on this product is available in the Material Safety Data Sheet (MSDS) as a guide to the precautions and safe handling of this product and its disposal. For further information, we recommend you review the MSDS. If handled correctly, there are no special precautions suggested.

Veedol Solucut – Key Differentiators

Market General Soluble Cutting Oil

Veedol Solucut

CORROSION RESISTANCE PERFORMANCE

Veedol Solucut provides excellent corrosion resistance on ferrous metal and alloys as compared to market general product



1%



5%



1%




5%

MICROBIAL GROWTH



Microbial growth observed due to unstable biocides



Veedol Solucut has very less or no microbial growth due to presence of stable biocides

EMULSION STABILITY - EMULSION FORMATION IN 400 PPM HARD WATER



Oil separation observed



Highly stable emulsion

Veedol Solucut has excellent emulsion stability thereby providing longer sump life in comparison to market general product

MULTI METAL CORROSION PROTECTION



Staining observed on Aluminium due to weaker additive composition



High performance additives prevent staining on Aluminium